

## FORMING METHOD FOR Al III-V COMPOUND SEMICONDUCTOR THIN FILM

## FORMING METHOD FOR Al III-V COMPOUND SEMICONDUCTOR THIN FILM

Patent Number: JP63266814  
Publication date: 1988-11-02  
Inventor(s): MORI KAZUO; others: 01  
Applicant(s): NEC CORP  
Requested Patent: ☐ JP63266814  
Application Number: JP19870099893 19870424  
Priority Number(s):  
IPC Classification: H01L21/205  
EC Classification:  
EC Classification:  
Equivalents:

### Abstract

**PURPOSE:** To form an superthin film of Al III-V compound semiconductor by an atomic layer epitaxy by supplying in advance Al organic compound to a decomposing area to decompose the compound, condensing and removing generated sole aluminum, and then supplying the decomposed gas onto a substrate.

**CONSTITUTION:** A carbon tube 2 is mounted in a quartz reaction tube 1, and set at a predetermined temperature. Hydrogen gas of carrier gas 3 is fed from left to right to transport  $\text{Al}(\text{C}_2\text{H}_5)_2\text{Cl}$ . Carbon decomposition reaction accelerating plates 5 are arranged on a decomposing area 4 at the upstream of a substrate in the tube 2, and a carbon substrate holder 6 for placing the substrate 7 is provided at the downstream of the area. Then, above semiconductor thin film forming apparatus is used to grown AIAs on the substrate,  $\text{AsH}_3$  is introduced as group V element gaseous compound through a carbon bypass tube 8 bypassing the decomposing area to the periphery of the substrate. Thus, the extremely thin film of Al III-V compound semiconductor can be formed under good controllability.